

## 測試報告 Test Report

號碼(No.) : CY/2017/90104

日期(Date) : 2017/09/15

頁數(Page) : 1 of 3

中華紙漿股份有限公司  
CHUNG HWA PULP CORPORATION  
台北市中正區重慶南路二段51號12樓  
12F, NO. 51, SEC. 2, CHONGCING S. RD., JHONGZHENG DISTRICT, TAIPEI CITY 100, TAIWAN,  
R. O. C.



以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as) :

送樣廠商(Sample Submitted By) : 中華紙漿股份有限公司 (CHUNG HWA PULP CORPORATION)  
樣品名稱(Sample Description) : FOOD GRADE PAPERBOARD (食品級用紙)  
樣品材質(Sample Material) : 紙 (PAPERBOARD)  
應用於(Used For) : 鮮淨防油卡、雪白防油卡、防油卡 PERFORMANCE (GREASEPROOF C1S CARDBOARD、GRESASEPROOF C1S CARDBOARD MATT、GRESASEPROOF C1S CARDBOARD PERFORMANCE)  
收件日期(Sample Receiving Date) : 2017/09/06  
測試期間(Testing Period) : 2017/09/06 TO 2017/09/15

### 測試需求(Test Requested) :

客戶指定依據美國聯邦法規之藥物暨食品管理(FDA) 21 CFR 176.170(使用條件E)進行測試。測試項目請參閱測試結果表格。 / As specified by client, the sample(s) was/were tested according to U.S. Food and Drug Administration (FDA) 21 CFR 176.170 (Condition of use E) to conduct test. Please refer to result table for testing item(s).

測試結果(Test Results) : 請參閱下一頁 (Please refer to following pages).

  
Singh Hsiao / Supervisor  
Signed for and on behalf of  
SGS TAIWAN LTD.  
Chemical Laboratory - Taipei

# 測試報告 Test Report

號碼(No.) : CY/2017/90104

日期(Date) : 2017/09/15

頁數(Page) : 2 of 3

中華紙漿股份有限公司

CHUNG HWA PULP CORPORATION

台北市中正區重慶南路二段51號12樓

12F, NO. 51, SEC. 2, CHONGCING S. RD., JHONGZHENG DISTRICT, TAIPEI CITY 100, TAIWAN,  
R. O. C.



## 測試結果(Test Results)

測試部位(PART NAME)No. 1 : 白色紙板 (WHITE CARDBOARD)

通過(PASS)

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	MDL	結果 (Result)	限值 (Limit)
				No. 1	
蒸發殘渣 (正庚烷, 70°F, 30分鐘) / Extractives residue (n-Heptane, 70°F, 30 min)	mg/in <sup>2</sup>	依據美國FDA 21 CFR 176.170 condition E (2015). / According to US FDA 21 CFR 176.170 condition E (2015).	0.2	n. d.	0.5
可溶於氯仿的萃取物 (50% 乙醇, 120°F, 24小時) / Net chloroform-soluble extractives (50% Alcohol, 120°F, 24 hr)	mg/in <sup>2</sup>		0.2	n. d.	0.5
可溶於氯仿的萃取物 (8% 乙醇, 120°F, 24 小時) / Net chloroform-soluble extractives (8% Alcohol, 120°F, 24 hr)	mg/in <sup>2</sup>		0.2	n. d.	0.5
可溶於氯仿的萃取物 (水, 120°F, 24小時) / Net chloroform-soluble extractives (D.I. Water, 120°F, 24 hr)	mg/in <sup>2</sup>		0.2	n. d.	0.5

## 備註(Note) :

- 0.1wt% = 1000ppm ; mg/kg = ppm
- MDL = Method Detection Limit (方法偵測極限值)
- n. d. = Not Detected = below MDL (未檢出 / 低於MDL)

## 測試報告 Test Report

號碼(No.) : CY/2017/90104

日期(Date) : 2017/09/15

頁數(Page) : 3 of 3

中華紙漿股份有限公司

CHUNG HWA PULP CORPORATION


台北市中正區重慶南路二段51號12樓

12F, NO. 51, SEC. 2, CHONGCING S. RD., JHONGZHENG DISTRICT, TAIPEI CITY 100, TAIWAN,  
R. O. C.



\* 照片中如有箭頭標示，則表示為實際檢測之樣品/部位。  
(The tested sample / part is marked by an arrow if it's shown on the photo.)

### CY/2017/90104



\*\* 報告結尾 (End of Report) \*\*